



## Technical Data Sheet

# DOWSIL™ 799 EU Glaze and Go Sealant

### FEATURES & BENEFITS

- Neutral cure
- Low modulus, high elasticity
- Good unprimed adhesion to a variety of substrates
- Non-corrosive to metals
- Easy to apply and tool
- Low odor
- Confirms to ISO11600-F&G-25LM
- Resistant to ultra-violet radiation
- Contains fungicide

### APPLICATIONS

- DOWSIL™ 799 EU Glaze and Go Sealant is a one-part neutral curing, low modulus silicone sealant specially formulated for glazing and weathersealing of windows.
- DOWSIL 799 EU Glaze and Go Sealant offers durable adhesion to most porous and non-porous substrates including masonry, brick, aluminium, PVC, glass and glazed surfaces.
- DOWSIL 799 EU Glaze and Go Sealant is mold and mildew resistant.

### TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications.

CTM <sup>1</sup>	Property	Unit	Result
	Cure system		Neutral
	Application temperature	°C °F	+5 to +40 +41 to +104
097B	Specific gravity	g/ml	1.03
364C	Extrusion	g/min	90
155A	Penetration	1/10 mm	110
098	Skin-over time (23°C or 73.4°F, 50%R.H.)	minutes	12
095A	Tack-free time (23°C or 73.4°F, 50%R.H.)	minutes	18
663A Cure rate (23°C or 73.4°F, 50%R.H.)			
	1 day	mm	2.8
	3 days	mm	4.3
<b>2 mm thickness S2 dumb-bells (ASTM<sup>2</sup> D 412)</b>			
137A	E-Modulus 100%	MPa	0.31
137A	Tensile strength	MPa	1.3
137A	Elongation at break	%	600
<b>12x12x50 mm size T.A. joint (ISO<sup>3</sup> 8339/DIN<sup>4</sup> 52455-2)</b>			
677	E-modulus 100%	MPa	0.3
677	Tensile strength	MPa	0.55
677	Elongation at break	%	340
677	Failure mode, Cohesive Failure	%	100
99E	Hardness (Shore A)		16

<sup>1</sup>CTM: Corporate Test Method, copies of CTM's are available on request.

<sup>2</sup>ASTM: American Society for Testing and Materials

<sup>3</sup>ISO: International Standardization Organization

<sup>4</sup>DIN: Deutsche Industrie Norm

## TECHNICAL SPECIFICATIONS AND STANDARDS

- Conforms to SNJF
- DIN 18545 E
- ISO 11600 F 25LM mortar (primed)
- ISO 11600 G 25LM (Façades & Vitrages)
- EN 15651 - CE MARK



## HOW TO USE

### Surface preparation

Surfaces must be cleaned, dry and free from grease and dust. Non-porous surfaces, such as aluminum, glass etc., should be cleaned with a suitable solvent for the substrate.

Porous substrates such as concrete, brickwork, mortar, etc. must be mechanically cleaned from loose particles using a steel brush, sanding disc, or any similar means. The use of a primer is recommended to obtain durable adhesion performance on such porous substrates, or if water immersion is expected to occur during the service life of the assembly. Otherwise, primers are not usually required but might be needed for some specific substrates to achieve optimum adhesion.

### Priming

This product adheres to a variety of porous and non-porous substrates.

Users must carry out their own tests due to the great variety of substances. In many cases, adhesion can be improved by pretreatment of the substrates with a primer:

- DOWSIL™ 1200 OS for metals
- DOWSIL™ Primer P for concrete and brick

### How to apply

DOWSIL 799 EU Glaze and Go Sealant is ready to use. After suitable joint preparation and masking, the sealant is gunned into place and tooled within 5 to 10 minutes using a spatula or tooling instrument.

After tooling, tooling aids and masking tape should be immediately removed.

DOWSIL 799 EU Glaze and Go Sealant cures reacting with atmospheric moisture. Typical properties are given for testing conditions of 23°C (73.4°F) and 50% R.H.

Uncured material can be removed by using a solvent. Cured material may be removed by abrasion or other mechanical means.

### Joint design

The sealant joint width should be designed to accommodate the movement capability of the sealant. In general, the minimum joint width should be 6 mm. For joints between 6–12 mm wide, a seal depth of 6 mm is recommended.

For joints above 12 mm wide, a width to depth ratio of 2:1 should be used, up to a maximum depth of 12 mm. For joint dimensions greater than 25 mm, please contact your local technical service department.

In situations where fillet joints are needed, a minimum of 6 mm sealant bite to each substrate is recommended. Bond beaker tape or a backer rod should be used as back-up material to provide backpressure and avoid three-sided adhesion that limits sealant movement capability.

## HANDLING PRECAUTIONS PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS

**AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.**

## USABLE LIFE AND STORAGE

When stored at or below 30°C (86°F) in the original unopened containers, this product has a usable life of 12 months from the date of production.

## PACKAGING INFORMATION

This product is available in 205 kg drums, 310 ml cartridges, 400 and 600 ml sausages.

## LIMITATIONS

Do not use DOWSIL 799 EU Glaze and Go Sealant in totally confined space because the sealant requires atmospheric moisture to cure. Bleeding can occur on porous substrates such as concrete, marble, granites and other natural stones. On these sensitive substrates, specific testing should be carried out.

DOWSIL 799 EU Glaze and Go Sealant must be properly stored prior to use.

DOWSIL 799 EU Glaze and Go Sealant is not recommended for structural glazing or insulated glazing applications. DOWSIL 799 EU Glaze and Go Sealant is neither tested nor represented as suitable for medical or pharmaceutical uses.

## HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and

regulatory compliance specialists  
available in each area.

For further information, please see our  
website, [www.consumer.dow.com](http://www.consumer.dow.com) or  
consult your local Dow representative.

**LIMITED WARRANTY  
INFORMATION – PLEASE  
READ CAREFULLY**

The information contained herein is  
offered in good faith and is believed to  
be accurate. However, because  
conditions and methods of use of our  
products are beyond our control, this  
information should not be used in  
substitution for customer's tests to  
ensure that our products are safe,  
effective, and fully satisfactory for the  
intended end use. Suggestions of use  
shall not be taken as inducements to  
infringe any patent.

Dow's sole warranty is that our  
products will meet the sales  
specifications in effect at the time of  
shipment.

Your exclusive remedy for breach of  
such warranty is limited to refund of  
purchase price or replacement of any  
product shown to be other than as  
warranted.

**TO THE FULLEST EXTENT  
PERMITTED BY APPLICABLE  
LAW, DOW SPECIFICALLY  
DISCLAIMS ANY OTHER  
EXPRESS OR IMPLIED  
WARRANTY OF FITNESS FOR A  
PARTICULAR PURPOSE OR  
MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY  
FOR ANY INCIDENTAL OR  
CONSEQUENTIAL DAMAGES.**

[www.consumer.dow.com](http://www.consumer.dow.com)

